

## Characteristics

Made from non-latex, polychloroprene synthetic polymer, these new surgical gloves offer all of the benefits of natural rubber latex, with none of the allergen problems associated with latex. The unique formulation allows them to be worn for extended periods without hand fatigue. Slightly roughened finish provides the ideal combination of gripping ability and tactility.



**Surgical Glove  
Sterile**

**DermAssist® Prestige®**

**Chloroprene  
Series 134**



## PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
5.5	134550	25 pairs/box, 4 boxes/case	Gloves, Surgical, Polychloroprene, Sterile, Powder-Free, Textured
6	134600	25 pairs/box, 4 boxes/case	
6.5	134650	25 pairs/box, 4 boxes/case	
7	134700	25 pairs/box, 4 boxes/case	
7.5	134750	25 pairs/box, 4 boxes/case	
8	134800	25 pairs/box, 4 boxes/case	
8.5	134850	25 pairs/box, 4 boxes/case	
9	134900	25 pairs/box, 4 boxes/case	

### Features

- Polymer Coated
- Bisque Finish
- Unique Polychloroprene Formulation

### Benefits

- Damp-hand Donnability
- Enhanced Grip
- Superior Comfort

*Product Solutions You Trust*



## DermAssist® Prestige® Chloroprene

**NON-LATEX POWDER-FREE SURGICAL GLOVES**



### Product Attributes

- Polymer Coated
- Bisque Finish
- Unique Polychloroprene Formulation

### Benefits

- Damp-hand Donnability
- Enhanced Grip
- Superior Comfort

DermAssist® Prestige® is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D6977	Standard Specification for Polychloroprene Surgical Gloves
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens
ASTM D5712	Standard Test Method for Analysis of Aqueous Extractable Protein in Natural Rubber
ASTM D3577	Standard Specification for Rubber Surgical Gloves

Average Length	Average Palm Thickness	Average Finger Thickness
11.6 in ± 295 mm	5.1 mil ± 0.13 mm	5.9 mil ± 0.15 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	18.5	20.9
ASTM Requirement Min. (Mpa)	17	12
Elongation (%)	840	750
ASTM Requirement Min. (%)	650	490



**Intertek**

Innovative Healthcare Corporation  
is certified to ISO 13485:2003 QMS  
for medical devices.



*Product Solutions You Trust*

**1-800-272-1533**